

R35 SR HPR

Technical data according to EN 410 and EN 673

4 mm single

4 / 16 / 4 mm double

Corrected emissivity of uncoated glass surface

0.837

Solar Energy Transmission, τ_e	21 %	19 %
Solar Energy Reflection, ρ_e	41 %	36 %
Solar Energy Absorption, a_e	38 %	45 %

Visible Light Transmission, τ_V	28 %	26 %
Visible Light Reflection (External) , ρ_{Ve}	45 %	46 %
Visible Light Reflection (Internal) , ρ_{Vi}	45 %	46 %

Ultraviolet Transmission, τ_{UV}	< 1 %
Ultraviolet Rejection	> 99 %

g value	0.30	0.39
Shading Coefficient	0.34	0.46
Total Solar Energy Rejected	70 %	61 %
Glare Reduction	68 %	70 %

U value, single glazing (W/m ² .K)	5.3	-
U value, double glazing, Air filled (W/m ² .K)	-	2.6

Emissivity, ϵ_n	0.71
--------------------------	------

Thickness without liner	45 μ
-------------------------	----------

Film Colour / Appearance	Silver
Installation position	Interior
Warranty	7 years**

Installation Notes: Use Film On for installation.

* Please check the complete Film to Glass Thermal Stress Compatibility Guidelines **before** film installation. ** Contact Solutia Performance Films for full details. All values for engineering parameters are determined by the manufacturer and independent testing laboratories.

R35 SR HPR

Features & Benefits

- Reflective solar control and privacy film
- Significant improvement of working conditions due to a high reduction in solar heat gain
- Reduction in air-conditioning costs and hence a reduction in energy costs
- Daylight privacy – ‘one way’ mirror
- Good glare reduction
- Excellent anti-UV protection integral to the polyester: helps to reduce fading of textiles, furniture, and works of art
- Scratch resistant coating: Excellent resistance to scratching and abrasion, increasing longevity and allowing easy cleaning
- Also available as Safety Film
- Interior installation

R35 SR HPR Spectra

